

**CLIENT:**

<b>Company:</b>	Artificial Grass Liquidators
<b>Address:</b>	PO Box 1627 Temecula, CA 92593
<b>Requested By:</b>	Dillon Georgian

**TEST MATERIAL:**

<b>Date Material Received:</b>	April 14, 2020
<b>Material Type:</b>	Synthetic Turf
<b>Material Condition:</b>	Excellent, New
<b>Material ID:</b>	Pro 48

**TESTING METHODS REQUESTED:**

<i>Testing Services Inc. was instructed by the client to test for the following...</i>	
<b>Standard:</b>	ASTM D1335
<b>Test Method:</b>	Standard Test Method for Tuft Bind Strength of Pile Yarn Floorcoverings

**SAMPLING PLAN:**

<b>Sampling Date:</b>	4/14/2020
<ul style="list-style-type: none"> <li>Specimen sampling is performed in the sampling department at TSI.</li> <li>The sampling size of specimens is determined by the test method requirements.</li> <li>In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.</li> <li>All samples are subjected to the outside environmental conditions of temperature and relative humidity.</li> <li>Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested</li> </ul>	

**DEVIATION FROM TEST METHOD:**

<b>State reason for any Deviation from, Additions to, or Exclusions From Test Method.</b>
None

**TEST SUMMARY:**

TEST METHOD	TEST DESCRIPTION	TEST RESULT							
ASTM D1335-17e1	Average Tuft Bind Strength	7.8 lbs/force							
<small>➤ Each individual pull was made on a combination of Monofilament fibers and textured fibers, same needle site</small>									
Pull #1	7.248 lbs/force	Pull #2	7.168 lbs/force	Pull #3	7.517 lbs/force	Pull #4	7.087 lbs/force	Pull #5	8.671 lbs/force
Pull #6	7.034 lbs/force	Pull #7	7.302 lbs/force	Pull #8	8.322 lbs/force	Pull #9	7.114 lbs/force	Pull #10	7.168 lbs/force
Pull #11	7.034 lbs/force	Pull #12	8.698 lbs/force	Pull #13	8.027 lbs/force	Pull #14	9.181 lbs/force	Pull #15	9.074 lbs/force

**Uncertainty:**

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

**Test Report Approval:**



Erle Miles, III, Lab Director Testing Services (TSI) LLC

**TSi Accreditation:**

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSi is an Organizational Member of ASTM (American Society for Testing and Materials). TSi is a certified independent testing laboratory by the STC (Synthetic Turf Council).

