

**CLIENT:**

<b>Company:</b>	Artificial Grass Liquidators
<b>Address:</b>	PO Box 1627 Temecula, CA 92593
<b>Requested By:</b>	Dillon Georgian

**TEST MATERIAL:**

<b>Date Material Received:</b>	April 14, 2020
<b>Material Type:</b>	Synthetic Turf
<b>Material Condition:</b>	Excellent, New
<b>Material ID:</b>	Pro RM50

**TESTING METHODS REQUESTED:**

<i>Testing Services Inc. was instructed by the client to test for the following...</i>			
<b>Standard:</b>	ASTM G154	<b>Test Method:</b>	Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of Non-Metallic Material

**SAMPLING PLAN:**

<b>Sampling Date:</b>	4/14/2020
<ul style="list-style-type: none"> <li>Specimen sampling is performed in the sampling department at TSI.</li> <li>The sampling size of specimens is determined by the test method requirements.</li> <li>In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.</li> <li>All samples are subjected to the outside environmental conditions of temperature and relative humidity.</li> <li>Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested</li> </ul>	

**DEVIATION FROM TEST METHOD:**

<b>State reason for any Deviation from, Additions to, or Exclusions From Test Method.</b>
None

**TEST SUMMARY:**


TEST METHOD	TEST DESCRIPTION	TEST RESULTS			
		500 Hours Exposure	1000 Hours Exposure	1500 Hours Exposure	2000 Hours Exposure
ASTM G154-16	QUV Accelerated Weathering	Color: 10 Texture: 10	Color: 10 Texture: 10	Color: 10 Texture: 10	Color: 10 Texture: 10

Change Rating:	10: Negligible or No Effect 9: Very Slight 8: Slight 6: Moderate 4: Pronounced 2: Severe 0: Very Severe	Test Equipment: QUV/se UVA-340 lamps, 0.77 W/m <sup>2</sup> 16 hours UV light @ 60°C 8 hours condensation @ 50°C Light Cycle: Continuous	*Ratings and comments are based on guidelines provided by Q Labs.
----------------	---	--	---

**Uncertainty:**

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

**Test Report Approval:**

 Digitally signed by Erle Miles  
 DN: cn=Erle Miles, o=Testing Services Inc., ou, email=erle@testing-services-usa.com, c=US  
 Date: 2020.08.14 09:21:54 -0400  
 Erle Miles, III, Lab Director Testing Services (TSI) LLC

**TSI Accreditation:** Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSI is an Organizational Member of ASTM (American Society for Testing and Materials). TSI is a certified independent testing laboratory by the STC (Synthetic Turf Council).

