

LABORATORY TEST REPORT

est Number: **Report Date:**

3192-3347 August 14, 2020

ASTM G154 QUV Accelerated Weathering

www.testingservices-usa.com • (706)226-1400 office@testingservices-usa.com

CLIENT:

V = 1 = 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1		
Company:	Artificial Grass Liquidators	
Address:	PO Box 1627	
	Temecula, CA 92593	
Requested By:	Dillon Georgian	

TEST MATERIAL:

Date Material Received:	April 14, 2020
Material Type:	Synthetic Turf
Material Condition:	Excellent, New
Material ID:	Cloud Nine

TESTING METHODS REQUESTED:

Testing Services Inc. was instructed by the client to test for the following				
Standard:	ASTM G154	Test Method:	Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of Non-Metallic Material	

SAMPLING PLAN:

Sampling Date: 4/14/2020	Sampling Date: 4/14/2020
--------------------------	--------------------------

- Specimen sampling is performed in the sampling department at TSI.
- The sampling size of specimens is determined by the test method requirements.
- In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.
- All samples are subjected to the outside environmental conditions of temperature and relative humidly.
- Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.				
	None			

TEST SUMMARY:

	TEST DESCRIPTION	TEST RESULTS			
TEST METHOD		500 Hours	1000 Hours	1500 Hours	2000 Hours
		Exposure	Exposure	Exposure	Exposure
ACTM C154 16	ASTM G154-16 QUV Accelerated Weathering	Color: 10	Color: 10	Color: 10	Color: 10
ASTIVI G 154-10 QUV Accelerated Weat	QOV Accelerated Weathering	Texture: 10	Texture: 10	Texture: 10	Texture: 10

Change Rating: 10: Negligible or No Effect Test Equipment: QUV/se 9: Very Slight UVA-340 lamps, 0.77 W/m² 8: Slight 16 hours UV light @ 60°C 6: Moderate 8 hours condensation @ 50°C Light Cycle: Continuous

4: Pronounced 2: Severe

0: Very Severe *Ratings and comments are based on guidelines provided by Q Labs.

<u>Uncertainty:</u>
We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:



Erle Miles, III, Lab Director Testing Services (TSI) LLC

TSi Accreditation:

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0 TSi is an Organizational Member of ASTM (American Society for Testing and Materials). TSi is a certified independent testing laboratory by the STC (Synthetic Turf Council).



Testing Services (TSI) LLC 817 Showalter Avenue PO Box 1343 Dalton, GA 30721