

# **LABORATORY TEST REPORT**

Test Number: **Report Date:** 

3192-3342 August 14, 2020

# **ASTM G154 QUV Accelerated Weathering**

www.testingservices-usa.com • (706)226-1400 office@testingservices-usa.com

#### CLIENT:

Company:	Artificial Grass Liquidators PO Box 1627		
Address:			
	Temecula, CA 92593		
Requested By:	Dillon Georgian		

### **TEST MATERIAL:**

1201 111/12111/121		
Date Material Received:	April 14, 2020	
Material Type:	Synthetic Turf	
Material Condition:	Excellent, New	
Material ID:	Hydro 98 Olive	

#### **TESTING METHODS REQUESTED:**

Testing Services Inc. was instructed by the client to test for the following						
Standard:	ASTM G154	Test Method:	Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of Non-Metallic Material			

#### **SAMPLING PLAN:**

Sampling Date:	4/14/2020
----------------	-----------

- Specimen sampling is performed in the sampling department at TSI.
- The sampling size of specimens is determined by the test method requirements.
- In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.
- All samples are subjected to the outside environmental conditions of temperature and relative humidly.
- Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

#### **DEVIATION FROM TEST METHOD:**

DETINITION TEST METHOD				
State reason for any Deviation from, Additions to, or Exclusions From Test Method.				
None				

#### **TEST SUMMARY:**

	TEST DESCRIPTION	TEST RESULTS			
TEST METHOD		500 Hours	1000 Hours	1500 Hours	2000 Hours
		Exposure	Exposure	Exposure	Exposure
ASTM G154-16	ASTM G154-16 QUV Accelerated Weathering	Color: 10	Color: 10	Color: 9	Color: 9
A31W G134-10	QOV Accelerated Weathering	Texture: 10	Texture: 10	Texture: 10	Texture: 10

Change Rating: 10: Negligible or No Effect Test Equipment: QUV/se 9: Very Slight UVA-340 lamps, 0.77 W/m<sup>2</sup> 8: Slight 16 hours UV light @ 60°C 6: Moderate 8 hours condensation @ 50°C Light Cycle: Continuous

4: Pronounced 2: Severe

0: Very Severe \*Ratings and comments are based on guidelines provided by Q Labs.

<u>Uncertainty:</u>
We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

## Test Report Approval:



Erle Miles, III, Lab Director Testing Services (TSI) LLC

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0 TSi is an Organizational Member of ASTM (American Society for Testing and Materials). TSi is a certified independent testing laboratory by the STC (Synthetic Turf Council)





Testing Services (TSI) LLC 817 Showalter Avenue PO Box 1343 Dalton, GA 30721